

## METHODOLOGY FOR APPLICATION OF MYK INDUFLOOR IB 1240

### Description:

**MYK Indufloor IB 1240** is a two component, solvent free Epoxy resin primer for Oil contaminated area. It bond very well to the damp concrete substrates.

**Packing:** 15 Kg Pack

### Methodology for Application:

**Step-1:-** Mixing of **MYK Indufloor IB 1240**

**Step-2:-** Application of **MYK Indufloor IB 1240**

### Mixing of MYK Indufloor IB 1240:

Stir the Hardener and Resin individually with drill mixer of proper size. Then add the entire content of the hardener into Resin container and stir the two components thoroughly using a low speed mixer for about 2 to 3 Minutes until a uniform color of the mixture is obtained.

### Application of MYK Indufloor IB 1240:

The mixed material is to be applied on the well-prepared surface by using stiff block with a rubbing brush in action.

### Application Areas:

Oily surfaces, Concrete slab and cement based screed subjected to negative pressure.

### Coverage:

0.670 -1 kg per m<sup>2</sup>

### Protection:

**MYK Indufloor IB 1240** should be applied with gloves and care should be taken to see that it doesn't fall on screen or eyes. Splashes on the eyes have to be immediately washed with plenty of water and medical advice to be taken.

**Note:** - All coverages mentioned above are theoretical and under laboratory conditions, MYK Schomburg strongly recommends actual site trials to ascertain actual coverages.