

METHODOLOGY FOR APPLICATION OF MYK INDUFLOOR IB 1250

Description:

MYK Indufloor IB 1250 is a two component, solvent free Epoxy resin primer which used as a barrier for moisture and water vapour on concrete surface.

Packing: 10 & 30 Kg Pack

Methodology for Application:

Step-1:- Mixing of **MYK Indufloor IB 1250**

Step-2:- Application of **MYK Indufloor IB 1250**

Mixing of MYK Indufloor IB 1250:

Stir the Hardener and Resin individually with drill mixer of proper size. Then add the entire content of the hardener into Resin container and stir the two components thoroughly using a low speed mixer for about 2 to 3 Minutes until a uniform color of the mixture is obtained.

Application of MYK Indufloor IB 1250:

The mixed material is to be applied on the well-prepared surface by using stiff block with a rubbing brush in action.

Application Areas:

Moisture areas, Concrete slab and cement based screed subjected to negative pressure.

Coverage:

0.4-0.6 Kg per m²

Protection:

MYK Indufloor IB 1250 should be applied with gloves and care should be taken to see that it doesn't fall on screen or eyes. Splashes on the eyes have to be immediately washed with plenty of water and medical advice to be taken.

Note: - All coverages mentioned above are theoretical and under laboratory conditions, MYK Schomburg strongly recommends actual site trials to ascertain actual coverages.