

## METHODOLOGY FOR APPLICATION OF MYK INDUFLOOR 1260

### Description:

**MYK Indufloor 1260** is a two components, solvent free, transparent, low viscosity, and pore blocking Epoxy resin primer.

**Packing:** 10 & 30 Kg Pack

### Methodology for Application:

**Step-1:-** Mixing of **MYK Indufloor 1260**

**Step-2:-** Application of **MYK Indufloor 1260**

### Mixing of MYK Indufloor 1260:

Stir the Hardener and Resin individually with drill mixer of proper size. Then add the entire content of the hardener into Resin container and stir the two components thoroughly using a low speed mixer for about 2 to 3 Minutes until a uniform color of the mixture is obtained.

### Application of MYK Indufloor 1260:

The mixed material is to be applied on the well-prepared surface by using a stiff brush.

### Application Areas:

Production areas, ware houses, ramps, concrete floors etc.

### Coverage:

0.25-0.4 Kg per m<sup>2</sup>

### Protection:

**MYK Indufloor 1260** should be applied with gloves and care should be taken to see that it doesn't fall on screen or eyes. Splashes on the eyes have to be immediately washed with plenty of water and medical advice to be taken.

**Note:** - All coverages mentioned above are theoretical and under laboratory conditions, MYK Schomburg strongly recommends actual site trials to ascertain actual coverages.