

METHODOLOGY FOR APPLICATION OF MYK INDUFLOOR - IB 3351

Description:

MYK Indufloor - IB 3351 is two components, solvent free universal coating with high chemical and mechanical resistance and also provides a high compressive and flexural strength.

Packing: 30 Kg pack

Methodology for Application:

Step-1:- Priming the Surface (using the recommended primer)

Step-2:- Mixing of **MYK Indufloor - IB 3351**

Step-3:- Application of **MYK Indufloor - IB 3351**

Primer should be applied before doing the application of Coating.

Mixing of MYK Indufloor - IB 3351:

Stir the Hardener and Resin individually with drill mixer of proper size. Then add the entire content of the hardener into Resin container and stir the two components thoroughly using a low speed mixer for about 2 to 3 Minutes until a uniform color of the mixture is obtained.

Application of MYK Indufloor - IB 3351:

The mixed material is evenly applied on the primed surface either by roller or trowels.

Application Areas:

Heavy duty industrial areas, production area, ware houses, food industry, laundries, loading ramps etc.

Coverage:

1.4 -1.5 kg per m² @ 1mm thick.

Protection:

MYK Indufloor - IB 3351 should be applied with gloves and care should be taken to see that it doesn't fall on screen or eyes. Splashes on the eyes have to be immediately washed with plenty of water and medical advice has to be taken.

Note: - All coverages mentioned above are theoretical and under laboratory conditions, MYK Schomburg strongly recommends actual site trials to ascertain actual coverages.