

## METHODOLOGY FOR APPLICATION OF MYK INDUFLOOR - IB 3355

### Description:

**MYK Indufloor - IB 3355** is two components, solvent free universal coating with high chemical and mechanical resistance.

Packing: 30 Kg pack

### Methodology for Application:

**Step-1:-** Priming the Surface (using the recommended primer)

**Step-2:-** Mixing of **MYK Indufloor - IB 3355**

**Step-3:-** Application of **MYK Indufloor - IB 3355**

Primer should be applied before doing the application of Coating.

### Mixing of MYK Indufloor - IB 3355:

Stir the Hardener and Resin individually with drill mixer of proper size. Then add the entire content of the hardener into Resin container and stir the two components thoroughly using a low speed mixer for about 2 to 3 Minutes until a uniform color of the mixture is obtained.

### Application of MYK Indufloor - IB 3355:

The mixed material is evenly applied on the primed surface either by roller or trowels.

### Application Areas:

Heavy duty industrial areas, production area, ware houses, food industry, laundries, loading ramps, road way etc.

### Coverage:

1.4 -1.5 kg per m<sup>2</sup> @ 1mm thick.

### Protection:

**MYK Indufloor - IB 3355** should be applied with gloves and care should be taken to see that it doesn't fall on screen or eyes. Splashes on the eyes have to be immediately washed with plenty of water and medical advice to be taken.

**Note:** - All coverages mentioned above are theoretical and under laboratory conditions, MYK Schomburg strongly recommends actual site trials to ascertain actual coverages.