

METHODOLOGY FOR APPLICATION OF MYK INDUFLOOR SL1

Description:

MYK Indufloor SL1 is a three component solvent free pigmented Epoxy selflevelling system upto 1mm.

Packing: 5 Kg pack

Methodology for Application:

Step-1:- Priming the Surface

Step-2:- Mixing of **MYK Indufloor SL1**

Step-3:- Application of **MYK Indufloor SL1**

Primer should be applied before doing the application of Topping.

Mixing of MYK Indufloor SL1:

The preweighed packs of the three components resin, hardener and pigment have to be mixed individually for 3 to 4 minutes with slow speed drilling machine. The pigment should be added to the base and stirred for 30 seconds. Then add the hardener content to the base until an even colour is obtained.

Application of MYK Indufloor SL1:

The mixed material should be applied on the primed surface and spread it to the required thickness with a notch trowel. After spreading immediately the floor should be rolled with a spiked nylon roller to help release any entrapped air. The rolling should be carried out using a "Back & Forth" technique along the same path.

Coverage:

1.65 kg per m² @ 1mm thick.

Application Areas:

Laboratories, Clean rooms, Pharmaceuticals, Computer assembly units etc.

Protection:

MYK Indufloor SL1 should be applied with gloves and care should be taken to see that it doesn't fall on screen or eyes. Splashes on the eyes have to be immediately washed with plenty of water and medical advice to be taken.

Note: - All coverages mentioned above are theoretical and under laboratory conditions, MYK Schomburg strongly recommends actual site trials to ascertain actual coverages.