

METHODOLOGY FOR APPLICATION OF MYK INDUFLOOR SL2

Description:

MYK Indufloor SL2 is a four component solvent free pigmented Epoxy selflevelling system for 2mm and above.

Packing: 17 Kg Pack

Step-1:- Priming the Surface

Step-2:- Mixing of **MYK Indufloor SL2**

Step-3:- Application of **MYK Indufloor SL2**

Primer should be applied before doing the application of Topping.

Mixing of MYK Indufloor SL2:

The preweighed packs of four components resin, hardener, filler and colour paste have to be mixed individually for 3 to 4 minutes with slow speed drilling machine. The colour paste should be added to the base and stirred for 30 seconds. Then add the hardener content to the base until an even colour and texture is obtained. Now add the filler content to the mixture and stirred slowly for 3 to 4 minutes until a homogeneous mass of uniform colour is obtained.

Application of MYK Indufloor SL2:

The mixed material should be applied on the primed surface and spread it to the required thickness with a notch trowel. After spreading immediately the floor should be rolled with a spiked nylon roller to help release any entrapped air. The rolling should be carried out using a "Back & Front" technique along the same path.

Coverage:

1.65 Kg per m² @ 1mm thick.

Application Areas:

Laboratories, Food processing units, Clean rooms, Pharmaceuticals, Computer assembly units etc.

Protection:

MYK Indufloor SL2 should be applied with gloves and care should be taken to see that it doesn't fall on screen or eyes. Splashes on the eyes have to be immediately washed with plenty of water and medical advice to be taken.

Note: - All coverages mentioned above are theoretical and under laboratory conditions, MYK Schomburg strongly recommends actual site trials to ascertain actual coverages.