

METHODOLOGY FOR APPLICATION OF MYK Bond EBA

Description:

MYK Bond EBA is a solvent free epoxy resin, bonding agent which is supplied in two component in pre-weighed quantities for ready to mix and use condition with high bond strength.

Packing: 1 and 3 Kg pack

Methodology for Application:

Step-1:- Mixing of **MYK Bond EBA**

Step-2:- Application of **MYK Bond EBA**

Mixing of MYK Bond EBA:

Stir the Hardener and Resin individually with drill mixer of proper size. Then add the entire content of the hardener into Resin container and stir the two components thoroughly using a low speed mixer for about 2 to 3 Minutes until a uniform color of the mixture is obtained.

Application of MYK Bond EBA:

The mixed **MYK Bond EBA** should be applied by brush properly and evenly over the well prepared surface. The new concrete has to be placed within 6 to 8 Hrs depending on the temperature.

Application Areas:

Used for horizontal & vertical surfaces, ideal for the extensions and structural repairs in structural concrete buildings, bridges, roads, loading bays etc.

Coverage:

4-5 m² per Kg

Protection:

MYK Bond EBA should be applied with gloves and care should be taken to see that it doesn't fall on screen or eyes. Splashes on the eyes have to be immediately washed with plenty of water and medical advice to be taken.

Note: - All coverages mentioned above are theoretical and under laboratory conditions, MYK Schomburg strongly recommends site trials to ascertain actual coverages.