

METHODOLOGY FOR APPLICATION OF MYK Coat 1010

Description:

MYK Coat 1010 is a two component, solvent based, low viscosity, water vapour permeable Epoxy resin concrete impregnator.

Packing: 4 Kg pack

Methodology for Application:

Step-1:- Mixing of **MYK Coat 1010**

Step-2:- Application of **MYK Coat 1010**

Mixing of MYK Coat 1010:

Stir the Hardener and Resin individually with drill mixer of proper size. Then add the entire content of the hardener into Resin container and stir the two components thoroughly using a low speed mixer for about 2 to 3 Minutes until a uniform color of the mixture is obtained.

Application of MYK Coat 1010:

MYK Coat 1010 can be applied by brush, roller or spray in two or three coats. The second coat is applied on the first coat when it is still wet.

Application Areas:

Concrete road ways, Parking lots above and below ground, Industrial floors, air port halls, workshop etc.

Coverage:

0.15- 0.4 Kg per m²

Protection:

MYK Coat 1010 should be applied with gloves and care should be taken to see that it doesn't fall on screen or eyes. Splashes on the eyes have to be immediately washed with plenty of water and medical advice to be taken

Note: - All coverages mentioned above are theoretical and under laboratory conditions, MYK Schomburg strongly recommends site trials to ascertain actual coverages.