

METHODOLOGY FOR APPLICATION OF MYK CRETE RN

Description:

MYK Crete RN is a polymer modified, flexible, shrinkage compensated mortar for interior and exterior use.

Packing: 25 Kg pack

Step-1:- Mixing of MYK Crete RN

Step-2:- Application of MYK Crete RN

Mixing of MYK Crete RN:

The preweighed material is to be mixed with 3.75 - 4 lits of water as per required consistency in a container and mixed with a mechanical mean until a homogeneous mass of uniform colour is obtained.

Application of MYK Crete RN:

The application is carried out on the prepared surface by using trowel to a desired thickness. The thickness should not be exceeding 20mm.

Application Areas:

Repair work of rupture and defects in wall and ceilings made of concrete and precast concrete.

Coverage:

Coverage varies with the thickness of application. Typically for 1 mm you will need 1.5 Kg per m².

Protection:

MYK Crete RN should be applied with gloves and care should be taken to see that it doesn't fall on screen or eyes. Splashes on the eyes have to be immediately washed with plenty of water and medical advice to be taken.

Note: - All coverages mentioned above are theoretical and under laboratory conditions, MYK Schomburg strongly recommends site trials to ascertain actual coverages.