

MYK FIX 10-S

Plug Cement

Technical Data Sheet

Properties:

FIX 10-S is a chloride free quick setting cement with immediate start of hardening after addition of water.

Scopes of use:

Subsequent sealing of surface leakage, water leaks and damp areas in cellars, manholes, tunnels, etc. against water and pressure water from the backside or frontside.

Technical Data:

Basis:	cement
Bulk weight:	1.2 gm/cc
Curing:	Immediately after addition of water
Supplied in:	1 Kg Pouch & 12 Kg Bag
Storage:	dry and air tight up to 12 months

Post treatment:

24 hours after the sealing a finish under addition of ASOPLAST-MZ may be applied.

After further 24 hours THERMOPAL®-SR44 restoration plaster in a thickness of layer of 2 cm may be processed.

Note:

Pilot testing is necessary.

FIX 10-S contains cement and is classified irritant according to GefStoffV.

Protection gloves have to be worn.

Please notice valid EU-safety data sheet.

Surface:

The surface has to be loadable and clean. Paints, brittle plaster, screed etc., have to be removed up to the solid ground (concrete, masonry). Dry areas have to be wetted. For interior sealing light weight blocks have to be pre-treated with a loadable cement plaster. Sealing of aerated concrete blocks or elements is not possible.

Instructions for use:

Sealing of leakage:

Leaking parts in sealed surfaces may be closed by pressing FIX 10-S in dry form or mixed with water into the leakage. FIX 10-S is to be pressed into the leak.

Sealing of large areas:

The wet but loadable surface is treated with AQUAFIN-F (consumption approx. 0.3 kg/m²), and sealed with AQUAFIN-1K (consumption 1.5 kg/m²) immediately. Into the green sealing FIX 10-S is rubbed until the surface is dry. (Consumption approx. 1.0 - 1.5 kg/m²). The powdered surface is painted again with AQUAFIN-F. Following a two-layer sealing with AQUAFIN-1K will be applied. If the surface tends to cracking AQUAFIN-2C is used in a thickness of layer of 2 - 4 mm instead of AQUAFIN-1K.

MYK SCHOMBURG INDIA PVT LTD

(An Indo-German JV)

8-2-703/A, 3rd Floor, Leela Gopal Towers,
Road No. 12, Banjara Hills,

Hyderabad -500 034

Tel: +91 40 3040 0000

email: mykschomburg.com

www.mykschomburg.com